CIVIL PRO
AN ISO 9001 : 2008 COMPANY &NABL ACCREDITED LABORATORY AS PER ISO/IEC 17025:2005
4, 7TH MAIN MALLESWARAM, BANGALORE -3
Certificate No.: TC-5548

Format No: CP/TF/01

TEST REPORT OF CEMENT CONCRETE CUBES

: **CP-2020-01-30-84** **Date: 20/11/2019**

: Improvements CC Road and Drain and Slabs at Kattigenahalli in Ward No.05 Byatarayanapura Sub Division

: Executive Engineer, KRIDL, Bangalore.

: EE(Project)/Ynk Zone/WO/65/2019-20

: 15-11-19

: Drain Bottom Salb Concrete

: 150X150X150 mm

: M20 / 7 Days Compressive Strength

: IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5

: 20/11/2019

[illegible]	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
[illegible]	M20	13/11/2019	20/11/2019	151.39 X 150.52 X 150.08	22788	**8.841**	420.6	18.5	18.4
[illegible]	M20	13/11/2019	20/11/2019	150.45 X 150.42 X 150.13	22630	**8.681**	409.0	18.1	
[illegible]	M20	13/11/2019	20/11/2019	150.06 X 150.50 X 151.08	22584	**8.639**	421.3	18.7	

CIVIL Pro Sig..... Date..... BANGALORE

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

****End of Report****

80 23444801 | e : rechan6630@yahoo.co.in, civilproexperts@gmail.com
BUILDING MATERIALS TESTING LABORATORY | STRUCTURAL | TECHNICAL | PROJECT MANAGEMENT | SURVEYING SERVICES |

Format No: CP/TF/01

TEST REPORT OF CEMENT CONCRETE CUBES

: **CP-2020-01-30-84** **Date: 11/12/2019**

: Improvements CC Road and Drain and Slabs at Kattigenahalli in Ward No.05 Byatarayanapura Sub Division

: Executive Engineer, KRIDL, Bangalore.

: EE(Project)/Ynk Zone/WO/65/2019-20

: 15-11-19

: Drain Bottom Salb Concrete

: 150X150X150 mm

: M20 / 28 Days Compressive Strength

: IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5

: 11/12/2019

Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
Drain Bottom Salb Concrete	M20	13/11/2019	11/12/2019	151.91 X 150.51 X 149.07	22864	**8.185**	528.7	23.1	23.1
Drain Bottom Salb Concrete	M20	13/11/2019	11/12/2019	150.80 X 149.24 X 149.30	22505	**8.804**	504.0	22.4	
Drain Bottom Salb Concrete	M20	13/11/2019	11/12/2019	150.28 X 151.14 X 150.68	22712	**8.147**	539.5	23.8	

FOR CIVIL Pro.

CIVIL Pro BANGALORE Sig..... Date.....

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

****End of Report****

Format No: CP/TF/01

TEST REPORT OF CEMENT CONCRETE CUBES

: **CP-2020-01-30-84** **Date: 20/11/2019**

: Improvements CC Road and Drain and Slabs at Kattigenahalli in Ward No.05 Byatarayanapura Sub Division

: Executive Engineer, KRIDL, Bangalore.

Reference : EE(Project)/Ynk Zone/WO/65/2019-20

: 15-11-19

: Drain Bottom Salb Concrete

Size : 150X150X150 mm

Age : M20 / 7 Days Compressive Strength

BIS codes : IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5

: 20/11/2019

Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
Drain Bottom Salb Concrete	M20	13/11/2019	20/11/2019	150.36 X 149.21 X 151.01	22434	**8.841**	410.5	18.3	18.5
Drain Bottom Salb Concrete	M20	13/11/2019	20/11/2019	150.49 X 151.14 X 149.05	22745	**8.681**	429.0	18.9	
Drain Bottom Salb Concrete	M20	13/11/2019	20/11/2019	149.39 X 149.82 X 150.64	22382	**8.639**	413.3	18.5	

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

****End of Report****

9972924526 | Tel : +91 80 23444801 | e : rechan6630@yahoo.co.in, civilproexperts@gmail.com

HIGHWAY & BUILDING MATERIALS TESTING LABORATORY | STRUCTURAL | GEO TECHNICAL | PROJECT MANAGEMENT | SURVEYING SERVICES |

Format No: CP/TF/01

TEST REPORT OF CEMENT CONCRETE CUBES

: **CP-2020-01-30-84** **Date: 11/12/2019**

: Improvements CC Road and Drain and Slabs at Kattigenahalli in Ward No.05 Byatarayanapura Sub Division

: Executive Engineer, KRIDL, Bangalore.

Reference : EE(Project)/Ynk Zone/WO/65/2019-20

: 15-11-19

: Drain Bottom Salb Concrete

: 150X150X150 mm

: M20 / 28 Days Compressive Strength

: IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5

: 11/12/2019

Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
Drain Bottom Salb Concrete	M20	13/11/2019	11/12/2019	149.81 X 149.28 X 149.66	22362	**8.185**	527.4	23.6	23.3
Drain Bottom Salb Concrete	M20	13/11/2019	11/12/2019	151.22 X 150.01 X 150.70	22684	**8.804**	521.0	23.0	
Drain Bottom Salb Concrete	M20	13/11/2019	11/12/2019	151.43 X 150.13 X 149.61	22735	**8.147**	534.2	23.5	

CIVIL PRO Sig..... Date.....

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

****End of Report****

4526 | Tel : +91 80 23444801 | e : rechan6630@yahoo.co.in, civilproexperts@gmail.com

HIGHWAY & BUILDING MATERIALS TESTING LABORATORY | STRUCTURAL | GEO TECHNICAL | PROJECT MANAGEMENT | SURVEYING SERVICES |

Format No: CP/TF/01

TEST REPORT OF CEMENT CONCRETE CUBES

: **CP-2020-01-30-84** **Date: 25/11/2019**

: Improvements CC Road and Drain and Slabs at Kattigenahalli in Ward No.05 Byatarayanapura Sub Division

: Executive Engineer, KRIDL, Bangalore.

: EE(Project)/Ynk Zone/WO/65/2019-20

: 20-11-19

: Drain Bottom Salb Concrete

: 150X150X150 mm

: M20 / 7 Days Compressive Strength

: IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5

: 25/11/2019

Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
Drain Bottom Salb Concrete	M20	18/11/2019	25/11/2019	149.59 X 149.55 X 150.50	22371	**8.841**	416.3	18.6	18.5
Drain Bottom Salb Concrete	M20	18/11/2019	25/11/2019	149.76 X 149.33 X 151.17	22364	**8.681**	415.9	18.6	
Drain Bottom Salb Concrete	M20	18/11/2019	25/11/2019	150.71 X 150.58 X 150.85	22693	**8.639**	414.8	18.3	

FOR CIVIL Pro.

CIVIL PRO Sig..... Date..... BANGALORE

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

****End of Report****

4526 | Tel : +91 80 23444801 | e : rechan6630@yahoo.co.in, civilproexperts@gmail.com

Format No: CP/TF/01

TEST REPORT OF CEMENT CONCRETE CUBES

: **CP-2020-01-30-84** **Date: 16/12/2019**

: Improvements CC Road and Drain and Slabs at Kattigenahalli in Ward No.05 Byatarayanapura Sub Division

: Executive Engineer, KRIDL, Bangalore.

: EE(Project)/Ynk Zone/WO/65/2019-20

: 20-11-19

: Drain Bottom Salb Concrete

: 150X150X150 mm

: M20 / 28 Days Compressive Strength

: IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5

: 16/12/2019

Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
Drain Bottom Salb Concrete	M20	18/11/2019	16/12/2019	150.11 X 151.53 X 150.41	22747	**8.185**	525.6	23.1	23.2
Drain Bottom Salb Concrete	M20	18/11/2019	16/12/2019	151.02 X 150.22 X 149.49	22686	**8.804**	517.3	22.8	
Drain Bottom Salb Concrete	M20	18/11/2019	16/12/2019	149.30 X 151.93 X 149.10	22684	**8.147**	534.4	23.6	

CIVIL PRO Sig..... Date.....

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

****End of Report****

Format No: CP/TF/01

TEST REPORT OF CEMENT CONCRETE CUBES

Date: 25/11/2019

: CP-2020-01-30-84

: Improvements CC Road and Drain and Slabs at Kattigenahalli in Ward No.05 Byatarayanapura Sub Division

: Executive Engineer, KRIDL, Bangalore.

: EE(Project)/Ynk Zone/WO/65/2019-20

: 20-11-19

: Drain Bottom Salb Concrete

: 150X150X150 mm

: M20 / 7 Days Compressive Strength

: IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5

: 25/11/2019

Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
Drain Bottom Salb Concrete	M20	18/11/2019	25/11/2019	149.24 X 151.09 X 149.85	22548	8.841	412.9	18.3	18.3
Drain Bottom Salb Concrete	M20	18/11/2019	25/11/2019	151.50 X 149.48 X 150.16	22647	8.681	415.1	18.3	
Drain Bottom Salb Concrete	M20	18/11/2019	25/11/2019	150.54 X 151.23 X 149.41	22766	8.639	416.8	18.3	

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

****End of Report****

4526 | Tel : +91 80 23444801 | e : rechan6630@yahoo.co.in, civilproexperts@gmail.com

CIVIL PRO
AN ISO 9001 : 2008 COMPANY &NABL ACCREDITED LABORATORY AS PER ISO/IEC 17025:2005
4, 7TH MAIN MALLESWARAM, BANGALORE -3
Certificate No.: TC-55

Format No: CP/TF/01

TEST REPORT OF CEMENT CONCRETE CUBES

: CP-2020-01-30-84 **Date: 16/12/2019**

: Improvements CC Road and Drain and Slabs at Kattigenahalli in Ward No.05 Byatarayanapura Sub Division

: Executive Engineer, KRIDL, Bangalore.

: EE(Project)/Ynk Zone/WO/65/2019-20

: 20-11-19

: Drain Bottom Salb Concrete

: 150X150X150 mm

: M20 / 28 Days Compressive Strength

: IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5

: 16/12/2019

Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
	M20	18/11/2019	16/12/2019	149.20 X 150.48 X 151.24	22451	**8.185**	518.1	23.1	23.1
	M20	18/11/2019	16/12/2019	151.56 X 149.17 X 151.81	22609	**8.804**	506.0	22.4	
	M20	18/11/2019	16/12/2019	151.30 X 150.98 X 150.43	22842	**8.147**	544.2	23.8	

18/2/2020

CIVIL PRO Sig..... Date.....

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

****End of Report****

4526 | Tel : +91 80 23444801 | e : rechan6630@yahoo.co.in, civilproexperts@gmail.com
HIGHWAY & BUILDING MATERIALS TESTING LABORATORY | STRUCTURAL | GEO TECHNICAL | PROJECT MANAGEMENT | SURVEYING SERVICES |

CIVIL PRO
AN ISO 9001 : 2008 COMPANY &NABL ACCREDITED LABORATORY AS PER ISO/IEC 17025:2005
4, 7TH MAIN MALLESWARAM, BANGALORE -3
Certificate No.: TC-55

Format No: CP/TF/01

TEST REPORT OF CEMENT CONCRETE CUBES

: **CP-2020-01-30-84** **Date: 25/11/2019**

: Improvements CC Road and Drain and Slabs at Kattigenahalli in Ward No.05 Byatarayanapura Sub Division

: Executive Engineer, KRIDL, Bangalore.

: EE(Project)/Ynk Zone/WO/65/2019-20

: 20-11-19

: Drain Bottom Salb Concrete

: 150X150X150 mm

: M20 / 7 Days Compressive Strength

: IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5

: 25/11/2019

Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
Drain Bottom Salb Concrete	M20	18/11/2019	25/11/2019	150.31 X 150.46 X 149.88	22616	**8.841**	425.2	18.8	18.6
Drain Bottom Salb Concrete	M20	18/11/2019	25/11/2019	149.21 X 150.81 X 150.99	22502	**8.681**	410.4	18.2	
Drain Bottom Salb Concrete	M20	18/11/2019	25/11/2019	151.28 X 149.48 X 149.93	22613	**8.639**	422.2	18.7	

CIVIL PRO Sig..... Date.....

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

****End of Report****

4526 | Tel : +91 80 23444801 | e : rechan6630@yahoo.co.in, civilproexperts@gmail.com

HIGHWAY & BUILDING MATERIALS TESTING LABORATORY | STRUCTURAL | GEO TECHNICAL | PROJECT MANAGEMENT | SURVEYING SERVICES |

Format No: CP/TF/01

TEST REPORT OF CEMENT CONCRETE CUBES

: **CP-2020-01-30-84** **Date: 16/12/2019**

: Improvements CC Road and Drain and Slabs at Kattigenahalli in Ward No.05 Byatarayanapura Sub Division

: Executive Engineer, KRIDL, Bangalore.

: EE(Project)/Ynk Zone/WO/65/2019-20

: 20-11-19

: Drain Bottom Salb Concrete

: 150X150X150 mm

: M20 / 28 Days Compressive Strength

: IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5

: 16/12/2019

Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
Drain Bottom Salb Concrete	M20	18/11/2019	16/12/2019	150.95 X 150.62 X 150.49	22736	**8.185**	542.9	23.9	23.2
Drain Bottom Salb Concrete	M20	18/11/2019	16/12/2019	150.98 X 149.71 X 151.18	22602	**8.804**	511.7	22.6	
Drain Bottom Salb Concrete	M20	18/11/2019	16/12/2019	150.60 X 150.97 X 151.36	22736	**8.147**	525.3	23.1	

CIVIL PRO TESTING & RESEARCH BANGALORE

CIVIL PRO Sig..... Date.....

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

****End of Report****

9972924526 | Tel : +91 80 23444801 | e : rechan6630@yahoo.co.in, civilproexperts@gmail.com

Format No: CP/TF/01

TEST REPORT OF CEMENT CONCRETE CUBES

Date: 30/11/2019

: CP-2020-01-30-84

: Improvements CC Road and Drain and Slabs at Kattigenahalli in Ward No.05 Byatarayanapura Sub Division

: Executive Engineer, KRIDL, Bangalore.

: EE(Project)/Ynk Zone/WO/65/2019-20

: 25-11-19

: Drain Side Wall Concrete

: 150X150X150 mm

: M20 / 7 Days Compressive Strength

: IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5

: 30/11/2019

Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
Drain Side Wall Concrete	M20	23/11/2019	30/11/2019	150.51 X 150.85 X 151.43	22704	**8.841**	425.1	18.7	18.7
Drain Side Wall Concrete	M20	23/11/2019	30/11/2019	151.22 X 149.31 X 151.41	22578	**8.681**	424.1	18.8	
Drain Side Wall Concrete	M20	23/11/2019	30/11/2019	149.48 X 151.36 X 149.62	22626	**8.639**	418.2	18.5	

FOR CIVIL Pro.

CIVIL PRO Sig..... Date..... BANGALORE

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

****End of Report****

Format No: CP/TF/01

TEST REPORT OF CEMENT CONCRETE CUBES

: **CP-2020-01-30-84** **Date: 21/12/2019**

: Improvements CC Road and Drain and Slabs at Kattigenahalli in Ward No.05 Byatarayanapura Sub Division

: Executive Engineer, KRIDL, Bangalore.

: EE(Project)/Ynk Zone/WO/65/2019-20

: 25-11-19

: Drain Side Wall Concrete

: 150X150X150 mm

: M20 / 28 Days Compressive Strength

: IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5

: 21/12/2019

Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
Drain Side Wall Concrete	M20	23/11/2019	21/12/2019	150.36 X 149.29 X 149.39	22447	**8.185**	516.7	23.0	23.3
Drain Side Wall Concrete	M20	23/11/2019	21/12/2019	151.69 X 151.67 X 149.55	23007	**8.804**	528.6	23.0	
Drain Side Wall Concrete	M20	23/11/2019	21/12/2019	150.82 X 149.60 X 151.09	22563	**8.147**	540.6	24.0	

FOR CIVIL Pro.

CIVIL PRO Sig..... Date..... BANGALORE

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

****End of Report****

Format No: CP/TF/01

TEST REPORT OF CEMENT CONCRETE CUBES

: **CP-2020-01-30-84** **Date: 30/11/2019**

: Improvements CC Road and Drain and Slabs at Kattigenahalli in Ward No.05 Byatarayanapura Sub Division

: Executive Engineer, KRIDL, Bangalore.

: EE(Project)/Ynk Zone/WO/65/2019-20

: 25-11-19

: Drain Side Wall Concrete

: 150X150X150 mm

: M20 / 7 Days Compressive Strength

: IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5

: 30/11/2019

Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
Drain Side Wall Concrete	M20	23/11/2019	30/11/2019	149.78 X 151.91 X 150.05	22754	**8.841**	417.1	18.3	18.2
Drain Side Wall Concrete	M20	23/11/2019	30/11/2019	150.61 X 150.25 X 149.12	22628	**8.681**	409.7	18.1	
Drain Side Wall Concrete	M20	23/11/2019	30/11/2019	151.93 X 149.28 X 151.92	22679	**8.639**	409.1	18.0	

CIVIL PRO Sig..... Date..... BANGALORE

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

****End of Report****

Format No: CP/TF/01

TEST REPORT OF CEMENT CONCRETE CUBES

: **CP-2020-01-30-84** **Date: 21/12/2019**

: Improvements CC Road and Drain and Slabs at Kattigenahalli in Ward No.05 Byatarayanapura Sub Division

: Executive Engineer, KRIDL, Bangalore.

: EE(Project)/Ynk Zone/WO/65/2019-20

: 25-11-19

: Drain Side Wall Concrete

: 150X150X150 mm

: M20 / 28 Days Compressive Strength

: IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5

: 21/12/2019

	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
	M20	23/11/2019	21/12/2019	151.62 X 149.26 X 150.45	22631	**8.185**	540.1	23.9	23.1
	M20	23/11/2019	21/12/2019	151.20 X 151.82 X 149.46	22955	**8.804**	509.3	22.2	
	M20	23/11/2019	21/12/2019	150.52 X 149.12 X 151.87	22445	**8.147**	525.0	23.4	

18/12/2020

CIVIL PRO Sig..... Date..... BANGALORE

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

****End of Report****

Format No: CP/TF/01

TEST REPORT OF CEMENT CONCRETE CUBES

: **CP-2020-01-30-84** **Date: 30/11/2019**

: Improvements CC Road and Drain and Slabs at Kattigenahalli in Ward No.05 Byatarayanapura Sub Division

: Executive Engineer, KRIDL, Bangalore.

Reference : EE(Project)/Ynk Zone/WO/65/2019-20

: 25-11-19

: Drain Side Wall Concrete

: 150X150X150 mm

: M20 / 7 Days Compressive Strength

BIS codes : IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5

: 30/11/2019

Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
Drain Side Wall Concrete	M20	23/11/2019	30/11/2019	149.14 X 150.46 X 149.46	22441	**8.841**	408.0	18.2	18.3
Drain Side Wall Concrete	M20	23/11/2019	30/11/2019	150.71 X 149.32 X 151.17	22505	**8.681**	415.8	18.5	
Drain Side Wall Concrete	M20	23/11/2019	30/11/2019	149.39 X 150.86 X 150.93	22537	**8.639**	410.5	18.2	

18/12/2020

CIVIL PRO Sig..... Date..... BANGALORE

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

****End of Report****